

Number of Components:	Two
Mix Ratio By Weight:	1:1
Specific Gravity:	
Part A	2.03
Part B	3.07
Pot Life:	2 Days
Shelf Life:	Six months at 23°C

Minimum Bond Line Cure Schedule*:	
150°C	5 Minutes

Product Description:

EPO-TEK[®] H20E-MP is a two component, 100% solids silver-filled epoxy system designed specifically for chip bonding in microelectronic and optoelectronic applications. It is also used extensively for thermal management applications due to its high thermal conductivity. It has proven itself to be extremely reliable over many years of service and is still the conductive adhesive of choice for new applications. Also available in a single component frozen syringe.

EPO-TEK[®] H20E Advantages & Application Notes:

- Designed specifically to meet the requirements pertaining to MIL-STD 883/Test Method 5011 for military hybrids.
- Processing info: It can be applied by many dispensing, stamping and screen printing techniques.
 - Dispensing: compatible with pressure/time delivery, auger screws, fluid jetting and G27 needles, in a single-component fashion.
 - Screen Printing: best using >200 metal mesh, with polymer squeegee blade with 80D hardness.
 - Stamping: small dots 6 mil in diameter can be realized.
- Misc / Other notes
 - Many technical papers written over 30-40 year lifetime. Contact techserv@epotek.com.
 - Over 1 trillion chips attached at a single company: no failures, Six Sigma and Certified Parts Supplier award winner.
 - Versatility in curing techniques including box oven, SMT style tunnel oven, heater gun, hot plate, IR, convection, or inductor coil.

Typical Properties: *(To be used as a guide only, not as a specification. Data below is not guaranteed. Different batches, conditions and applications yield differing results; Cure condition: 150°C/1 hour; *denotes test on lot acceptance basis)*

Physical Properties:

*Pot Life – MIL-STD 883/5011: Pass (<10% change after 1 hr)

*Color: Part A: Silver Part B: Silver

*Consistency: Smooth paste

*Viscosity (@ 100 RPM/23°C): 2,200 – 3,200 cPs

Thixotropic Index: 4.63

*Glass Transition Temp.(Tg): ≥ 80°C (Dynamic Cure:
20—200°C /ISO 25 Min; Ramp -10—200°C @ 20°C/Min)

Coefficient of Thermal Expansion (CTE):

Below Tg: 31 x 10⁻⁶ in/in/°C

Above Tg: 158 x 10⁻⁶ in/in/°C

Shore D Hardness: 75

Lap Shear Strength @ 23°C: 1,475 psi

*Die Shear Strength @ 23°C: > 5 Kg / 1,700 psi

Degradation Temp. (TGA): 425°C

Electrical Properties:

*Volume Resistivity @ 23°C: ≤ 0.0004 Ohm-cm

Thermal Properties:

Thermal Conductivity: 2.5 W/mK

Based on standard method: Laser Flash

Thermal Conductivity: 29 W/mK

Based on Thermal Resistance Data: $R = L \times K^{-1} \times A^{-1}$

Weight Loss:

*@ 200°C: 0.59%

@ 250°C: 1.09%

@ 300°C: 1.67%

Operating Temp:

Continuous: -55°C to 200°C

Intermittent: -55°C to 300°C

Storage Modulus @ 23°C: 808,700 psi

*Ions: Cl⁻ < 200 ppm

Na⁺ < 50 ppm

NH₄⁺ 126 ppm

K⁺ < 50 ppm

*Particle Size: ≤ 45 Microns

Thermal Resistance: (Junction to Case)

TO-18 package with nickel-gold metallized 20 x 20 mil chips and bonded with EPO-TEK[®] H20E (2 mils thick)

EPO-TEK[®] H20E: 6.7 to 7.0°C/W

Solder: 4.0 to 5.0°C/W

EPOXY TECHNOLOGY, INC.

14 Fortune Drive, Billerica, MA 01821-3972 Phone: 978.667.3805 Fax: 978.663.9782

www.EPOTEK.com

Epoxyes and Adhesives for Demanding Applications™

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

EPO-TEK[®] H20E-MP Suggested Applications

- **Semiconductor IC Packaging**
 - Die-attaching chips to leadframes; compatible with Si and MEM's chips, 260°C lead-free reflow and JEDEC Level I packaging requirements.
 - Capable of being snap cured in-line, as well as traditional box oven techniques.
 - Adhesive for solderless flip chip packaging and ultra fine pitch SMD printing.
- **Hybrid Micro-electronics**
 - A comparable alternative to solder and eutectic die attach, in terms of thermal performance; very commonly no more than 1-2°C/watt difference in thermal resistance.
 - Die-attaching of quartz crystal oscillators (QCO) to the Au posts of TO-can style lead-frame.
 - Used with GaAs chips for microwave/radar applications up to 77GHz.
 - SMD attach adhesive which can be cured simultaneously with die-attach processes.
 - Compatible with Au, Ag, Ag-Pd terminations of capacitors and resistor SMDs.
 - NASA approved low outgassing adhesive.
 - Adhesive for EMI and Rf shielding of Rf, microwave and IR devices.
- **Electronic & PCB Circuit Assembly**
 - Used to make electrical contacts in acoustical applications of speakers/microphones.
 - Electrical connection of piezo's to PCB. Pads of PZT are connected to many kinds of circuits using H20E, including ink jet heads, MEMs and ultrasound devices.
 - Automotive applications include pressure sensing and accelerometer circuits.
 - Electrically conductive adhesive (ECA) for connections of circuits to Cu coils in Rf antenna applications such as smart cards and RFID tags.
 - ECA for attaching SMDs to membrane switch flex circuits. Compatible with Ag-PTF and carbon graphite PCB pads. A low temperature "solder free" solution.
 - Solar-Photovoltaic industry
 - ECA for the electrical connection of transparent conductive oxide (TCO) to PCB pads.
 - Replacement of solder joints of Cu/Sn ribbon wire, from cell-to-cell; a common "solar cell stringing" adhesive.
 - Die-attach of III-V semiconductor chips to substrates used in solar concentrator technology, such as CdTe and GaAs.
 - An effective heat-sink on thermal substrates using Cu, BeO, aluminum nitride, etc.
 - Ability to be dispensed in high volumes via dots, arrays, and writing methods.
- **Medical Applications**
 - USP Class VI adhesive for circuits requiring implantation/biocompatibility.
 - Die-attaching photo diode arrays in X-ray circuits.
 - Vibration resistant adhesive for ultrasound applications < 20 MHz frequency; making the electrical connection of PZT to Au/PCB substrate.
 - Electrical connections of die, SMDs and QCO for pacemaker hybrid circuits.
 - A common ECA for hearing aid applications using hybrid, ECM or MEMs technology.
- **Opto-Electronic Packaging Applications**
 - Adhesive for fiber optic components using DIP, Butterfly or custom hybrid IC packages. As an ECA, it attaches waveguides, die bonds laser diodes and heat sinks the high power laser circuits.
 - Die-attaching IR-detector chips onto PCBs or TO-can style headers.
 - Die-attaching LED chips to substrates using single chip packages, or arrays.
 - Adhesion to Ag, Au and Cu plated leadframes and PCBs.
 - Electrical connection of ITO to PCBs found in LCD industry.
 - A low temp ECA for OLED displays and organically printable electronics.

EPOXY TECHNOLOGY, INC.

14 Fortune Drive, Billerica, MA 01821-3972 Phone: 978.667.3805 Fax: 978.663.9782

www.EPOTEK.com

Epoxies and Adhesives for Demanding Applications™