

Product Information Sheet

MATERIAL ID:

EPO-TEK® OD2002

Date: Jun 2010

Rev: VII

Material Description: High Tg version of EPO-TEK®353ND with low modulus and good toughness. Replacement for EPO-TEK® 364.

Number of Components: Two

Mix Ratio by Weight: 20:1

Cure Schedule (minimum): 150°C/5 Minutes - 120°C/15 Minutes - 100°C/30 Minutes

Specific Gravity: Part A: 1.20 Part B: 1/02

Pot Life: 4 Hours

Shelf Life: One year at room temperature

NOTE: Container(s) should be kept closed when not in use. Filled systems should be stirred thoroughly before mixing and prior to use.
-TOTAL MASS SHOULD NOT EXCEED 25 GRAMS -

MATERIAL CHARACTERISTICS: To be used as a guide only, not as a specification. Data below is not guaranteed. Different batches, conditions and applications yield differing results; Cure condition: 150°C/1 Hour

* denotes test on lot acceptance basis

PHYSICAL PROPERTIES:

* Color (before cure):	Part A: Cloudy	Part B: Amber	
* Consistency	Pourable paste		
* Viscosity (23°C): @ 2.5 rpm	24,000 - 42,000 cPs		
Thixotropic Index:	N/A		
* Glass Transition Temp:	> 140 °C (Dynamic Cure: 20—200°C /ISO 25 Min; Ramp -10—200°C @ 20°C/Min)		
Coefficient of Thermal Expansion (CTE):			
Below Tg:	45 x 10 ⁻⁶ in/in°C		
Above Tg:	187 x 10 ⁻⁶ in/in°C		
Shore D Hardness:	69		
Lap Shear @ 23°C:	1,570 psi		
Die Shear @ 23°C:	>10 Kg		3,400 psi
Degradation Temp:	443 °C		
Weight Loss:			
@ 200°C	< 0.05 %		
@ 250°C	< 0.05 %		
@ 300°C	< 0.05 %		
Operating Temp:			
Continuous:	- 55°C to	225 °C	
Intermittent:	- 55°C to	325 °C	
Storage Modulus:	263,291 psi		
Ion Content:			
Cl:	ppm	NA⁺:	ppm
NH₄⁺:	ppm	K⁺:	ppm
Particle Size:	N/A		

ELECTRICAL AND THERMAL PROPERTIES:

Thermal Conductivity:	N/A
Volume Resistivity @ 23°C:	> 2 x 10 ¹² Ohm-cm
Dielectric Constant (1KHz):	2.83
Dissipation Factor (1KHz):	0.011

OPTICAL PROPERTIES @ 23°C:

Spectral Transmission:	>98% @ 800 - 1640 nm	69% @ 600 nm
Index of Refraction:	1.5728 @ 589 nm	

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.