



Product Information Sheet

EPO-TEK® 354-T2

Date: July 2025
Rev: III
No. of Components: Two
Mix Ratio by Weight: 10 : 1
Specific Gravity: Part A: 1.12 Part B: 1.18
Pot Life: 3 Days
Shelf Life- Bulk: Six months at room temperature

Recommended Cure: 150°C / 1 Hour

Minimum Alternative Cure(s):

May not achieve performance properties listed below

150°C / 10 Minutes

120°C / 30 Minutes

80°C / 2 Hours

NOTES:

- Container(s) should be kept closed when not in use.
- Filled systems should be stirred thoroughly before mixing and prior to use.
- Performance properties (rheology, conductivity, others) of the product may vary from those stated on the data sheet when bi-pak/syringe packaging or post-processing of any kind is performed. Epoxy's warranties shall not apply to any products that have been reprocessed or repackaged from Epoxy's delivered status/container into any other containers of any kind, including but not limited to syringes, bi-paks, cartridges, pouches, tubes, capsules, films or other packages.
- Syringe packaging will impact initial viscosity and effective pot life, potentially beyond stated parameters.
- **TOTAL MASS SHOULD NOT EXCEED 25 GRAMS**

Product Description: EPO-TEK® 354-T2 is a two component, thixotropic, high Tg epoxy designed for semiconductor packaging in medical, fiber optic and optoelectronic assemblies. It is an electrically and thermally insulating epoxy and a more thixotropic version of EPO-TEK® 354-2.

Typical Properties: Cure condition: varies as required Different batches, conditions & applications yield differing results.

Data below is not guaranteed. To be used as a guide only, not as a specification.

Information is Preliminary While Specifications Are Being Developed.

PHYSICAL PROPERTIES:

Color (before cure):	Part A: Tan	Part B: Dark Amber
Consistency:	Smooth Thixotropic Paste	
Viscosity (23°C) @ 10 rpm:	20,008	cPs
Thixotropic Index:	2.85	
Glass Transition Temp:	111	°C (Dynamic Cure: 20-200°C/ISO 25 Min; Ramp -10-200°C @20°C/Min)
Coefficient of Thermal Expansion (CTE):		
	Below Tg:	68.6 x 10 ⁻⁶ in/in°C
	Above Tg:	393.7 x 10 ⁻⁶ in/in°C
Shore D Hardness:	82	
Die Shear @ 23°C:		Kg psi
Degradation Temp:	430	°C
Weight Loss:		
	@ 200°C:	0.02 %
	@ 250°C:	0.17 %
	@ 300°C:	0.45 %
Suggested Operating Temperature:	< 300	°C (Intermittent)
Storage Modulus:	286739.6	psi
Particle Size:	≤ 20	microns

OPTICAL PROPERTIES @ 23°C:

Spectral Transmission:	>90% @ 2100- 600	nm
Refractive Index:	1.5725	nm

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

EPOXY TECHNOLOGY, INC.

14 FORTUNE DRIVE, BILLERICA, MA 01821 (978) 667-3805, FAX (978) 663-9782

www.epotek.com