

**Product Information Sheet**  
**EPO-TEK® OD1001-67 White**

**Date:** February 2021  
**Rev:** V  
**No. of Components:** Single  
**Mix Ratio by Weight:** N/A  
**Specific Gravity:** 1.14  
**Pot Life:** 28 Days  
**Shelf Life- Bulk:** One year at -40°C

**Recommended Cure: 150°C / 1 Hour**

**NOTES:**

- Container(s) should be kept closed when not in use.
- Filled systems should be stirred thoroughly before mixing and prior to use.
- Performance properties (rheology, conductivity, others) of the product may vary from those stated on the data sheet when bi-pak/syringe packaging or post-processing of any kind is performed. Epoxy's warranties shall not apply to any products that have been reprocessed or repackaged from Epoxy's delivered status/container into any other containers of any kind, including but not limited to syringes, bi-paks, cartridges, pouches, tubes, capsules, films or other packages.

**Product Description:** A white pigmented version of EPO-TEK® OD1001-67. It is a single component, electrically insulating epoxy designed as a low stress underfill adhesive for large die. It is also a more flowable version of EPO-TEK® TD1001-67.

**Typical Properties:** Cure condition: 150°C / 1 Hour Different batches, conditions & applications yield differing results.  
 Data below is not guaranteed. To be used as a guide only, not as a specification. \* denotes test on lot acceptance basis

PHYSICAL PROPERTIES:			
* Color (before cure):	White		
* Consistency:	Smooth thin paste		
* Viscosity (23°C) @ 100 rpm:	1,200 - 2,000	cPs	
Thixotropic Index:	1.2		
* Glass Transition Temp:	≤ 15	°C (Dynamic Cure: 20-200°C/ISO 25 Min; Ramp -40-200°C @20°C/Min)	
Coefficient of Thermal Expansion (CTE):			
	Below Tg:	82	x 10 <sup>-6</sup> in/in°C
	Above Tg:	270	x 10 <sup>-6</sup> in/in°C
Shore A Hardness:	95		
Lap Shear @ 23°C:	> 2,000	psi	
Die Shear @ 23°C:	≥ 3	Kg	1,067 psi
Degradation Temp:	321 °C		
Weight Loss:			
	@ 200°C:	0.13	%
	@ 250°C:	0.49	%
	@ 300°C:	2.42	%
Suggested Operating Temperature:	< 250 °C (Intermittent)		
Storage Modulus:	164,628	psi	
* Particle Size:	≤ 20 microns		

**This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.**

EPOXY TECHNOLOGY, INC.  
 14 FORTUNE DRIVE, BILLERICA, MA 01821 (978) 667-3805, FAX (978) 663-9782  
[www.epotek.com](http://www.epotek.com)