



Product Information Sheet

EPO-TEK® T6065

Date: September 2017
Rev: III
No. of Components: Single
Mix Ratio by Weight: N/A
Specific Gravity: 1.68
Pot Life: 28 Days
Shelf Life- Bulk: One year at -40°C

Recommended Cure: 180°C / 1 Hour

NOTES:

- Container(s) should be kept closed when not in use.
- Filled systems should be stirred thoroughly before mixing and prior to use.
- Performance properties (rheology, conductivity, others) of the product may vary from those stated on the data sheet when bi-pak/syringe packaging or post-processing of any kind is performed. Epoxy's warranties shall not apply to any products that have been reprocessed or repackaged from Epoxy's delivered status/container into any other containers of any kind, including but not limited to syringes, bi-paks, cartridges, pouches, tubes, capsules, films or other packages.

Product Description: A single component, high Tg, thermally conductive, semiconductor die-attach grade epoxy. It was designed for bonding chips and SMD's inside hybrid micro-electronic packages. Other applications include JEDEC and opto-electronic packaging.

Typical Properties: Cure condition: 180°C / 1 Hour Different batches, conditions & applications yield differing results.

Data below is not guaranteed. To be used as a guide only, not as a specification. * denotes test on lot acceptance basis

PHYSICAL PROPERTIES:			
* Color (before cure):	White		
* Consistency:	Smooth paste		
* Viscosity (23°C) @ 2.5 rpm:	80,000-120,000	cPs	
Thixotropic Index:	1.9		
* Glass Transition Temp:	≥ 100	°C	(Dynamic Cure: 20-300°C/ISO 25 Min; Ramp -10-200°C @20°C/Min)
Coefficient of Thermal Expansion (CTE):			
Below Tg:	38	x 10 ⁻⁶	in/in°C
Above Tg:	136	x 10 ⁻⁶	in/in°C
Shore D Hardness:	92		
Lap Shear @ 23°C:	> 2,000	psi	
Die Shear @ 23°C:	≥ 20	Kg	7,112 psi
Degradation Temp:	397	°C	
Weight Loss:			
@ 200°C:	0.10	%	
@ 250°C:	0.16	%	
@ 300°C:	0.30	%	
Suggested Operating Temperature:	< 300	°C	(Intermittent)
Storage Modulus:	816,394	psi	
Ion Content:	Cl ⁻ : 135 ppm	Na ⁺ : 48 ppm	
	NH ₄ ⁺ : 105 ppm	K ⁺ : 6 ppm	
* Particle Size:	≤ 20	microns	

ELECTRICAL AND THERMAL PROPERTIES:		
Thermal Conductivity:	0.8	W/mK
Volume Resistivity @ 23°C:	≥ 1.2 x 10 ¹⁴	Ohm-cm
Dielectric Constant (1KHz):	5.30	
Dissipation Factor (1KHz):	0.011	

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

EPOXY TECHNOLOGY, INC.
14 FORTUNE DRIVE, BILLERICA, MA 01821 (978) 667-3805, FAX (978) 663-9782
www.epotek.com