



Product Information Sheet

EPO-TEK® 301-2FL-T

Date: February 2019
Rev: VIII
No. of Components: Single
Mix Ratio by Weight: N/A
Specific Gravity: 1.09
Pot Life: 5 Hours
Shelf Life- Syringe: Six months at -40°C

Recommended Cure: 80°C / 3 Hours

Minimum Alternative Cure(s):
May not achieve performance properties listed below
23°C / 72 Hours

NOTES:

- Container(s) should be kept closed when not in use.
- Filled systems should be stirred thoroughly before mixing and prior to use.
- Performance properties (rheology, conductivity, others) of the product may vary from those stated on the data sheet when bi-pak/syringe packaging or post-processing of any kind is performed. Epoxy's warranties shall not apply to any products that have been reprocessed or repackaged from Epoxy's delivered status/container into any other containers of any kind, including but not limited to syringes, bi-paks, cartridges, pouches, tubes, capsules, films or other packages.

Product Description: EPO-TEK® 301-2FL-T is a single component, optical grade, flexible epoxy resin. It is a thixotropic version of EPO-TEK® 301-2FL.

Typical Properties: Cure condition: 80°C / 3 Hours Different batches, conditions & applications yield differing results.
Data below is not guaranteed. To be used as a guide only, not as a specification. * denotes test on lot acceptance basis

PHYSICAL PROPERTIES:

* Color (before cure):	Cloudy/colorless
* Consistency:	Slightly thixotropic liquid
* Viscosity (23°C) @ 100 rpm:	300 - 600 cPs
Thixotropic Index:	3.2
* Glass Transition Temp:	≥ 40 °C (Dynamic Cure: 20-200°C/ISO 25 Min; Ramp -10-200°C @20°C/Min)
Shore D Hardness:	70
Die Shear @ 23°C:	≥ 5 Kg 1,778 psi
Degradation Temp:	336 °C
Weight Loss:	
@ 200°C:	0.84 %
@ 250°C:	1.24 %
@ 300°C:	3.26 %
Suggested Operating Temperature:	< 250 °C (Intermittent)
* Particle Size:	≤ 20 microns

OPTICAL PROPERTIES @ 23°C:

Spectral Transmission:	≥ 97% @ 380-2100 nm
Refractive Index:	1.5086 @589 nm

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

EPOXY TECHNOLOGY, INC.
14 FORTUNE DRIVE, BILLERICA, MA 01821 (978) 667-3805, FAX (978) 663-9782
www.epotek.com